



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสันส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

# SISCOFLOOR 1200 (L)

EPOXY MORTAR (SOLVENT FREE)

<b>PRODUCT DESCRIPTION</b>	A two component epoxy resin for use in flooring applications. It has been specially formulated to provide seamless, truly level floor surfaces with excellent chemical and abrasion resistance. It can be applied to dry or damp surfaces, it is can be mixed with quartz sand for adjust floor surfaces level.					
<b>SPECIFIC PROPERTIES</b>	Excellent chemical, impact and abrasion resistance. Solvent free – no aids ventilation requirements during application. Can be applied to damp surfaces. Suitable for applied at 1000-3000 microns DFT.					
<b>PHYSICAL DATA</b>	<b>Solids (% by volume)</b>	..100...%				
	<b>Dry Film Thickness</b>	1000-3000..microns				
	<b>Wet Film Thickness</b>	1000-3000..microns				
	<b>Flash Point</b>	> 90 °C				
	<b>Theoretical Coverage</b>	1.0 kg/m <sup>2</sup> /mm				
	<b>Colours</b>	Yellowish Clear				
	<b>Gloss</b>	Gloss				
<b>APPLICATION DATA</b>	<b>Application method</b>	Trowel, Brush, roller				
	<b>Temperature minimum</b>	5 °C				
	<b>Humidity Maximum</b>	85% R.H.				
	<b>Mixing Ratio</b>	2 Base : 1 Hardener (by weight)				
	<b>Drying Time</b>					
	<b>Surface Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<b>Over coating Interval</b>		<b>Pot Life</b>
				<b>Minimum</b>	<b>Maximum</b>	
	25 °C	6 Hrs	24 Hrs	24 Hrs	--	40 Mins
	30 °C	5 Hrs	16 Hrs	16 Hrs	--	30 Mins
	35 °C	4 Hrs	12 Hrs	12 Hrs	--	15 Mins
	To prolong pot life in hot condition, material should be mixed in small amount then pour on the floor for thin layer. (If mixed material was leaved in pail, it will be harden very fast)					
<b>ADDITIONAL INFORMATION</b>	Resistance to the following substances is extremely good, but in all cases of chemical spillage it is essential that the chemicals be removed as quickly as possible and the surface washed down with water. 10% Hydrochloric, 5% Nitric, 5% Phosphoric,10% Sulfuric, 28% Ammonium hydroxide, 10% Potassium hydroxide, 10% Sodium hydroxide, 6% Sodium hyperchorite, Diesel Fuel, Isopropanol, Kerosene, Naphtha, Salt water, Sewages, Xylene, Toluene, Aluminium Chloride(Dry), Tar, Starch, Sodium silicate, Lead Acetate, Magnesium bisulfate, magnesium chloride, Ethylene Glycol, ferrous sulfate, Zinc Sulfate etc. Cleaning Solvent Thinner No.9 Packaging Two pack product, 30 kg set (A+B) Preferable Preceding Coats Siscofloor 105, Siscofloor 105HB Preferable Subsequent Coats Siscofloor 5000, Floorguard 5500					
<b>SAFETY PRECAUTIONS</b>	Ensure that there is adequate ventilation in the area where the product is being applied. Do not breath vapour or spray. In case of touch skin, wash skin thoroughly soap and water. In case of accidental eyes splashes, flush eyes with warm water immediately and obtain medical advice.					
<b>DISCLAIMER</b>	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.					