



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสชั่นส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

SISCOFLOOR 105HB

EPOXY PRIMER FOR CONCRETE FLOOR

PRODUCT DESCRIPTION	A two component, Epoxy concrete primer for new concrete. It is good penetrate into concrete and promote and enhance adhesion of subsequent coatings.					
SPECIFIC PROPERTIES	Excellent inter-coat adhesion properties. Excellent water and alkali resistance performance. Can be Cured on wet concrete or high humidity concrete.					
PHYSICAL DATA	Solids (% by volume)	. 60...%				
	Dry Film Thickness	48-60. microns				
	Wet Film Thickness	80-100.microns				
	Flash Point	> 40 °C				
	Theoretical Coverage	0.1-0.2 kg/m ²				
	Colours	Yellowish Clear				
	Gloss	Gloss				
APPLICATION DATA	Application method	Air spray, Brush, roller				
	Temperature minimum	0 °C				
	Humidity Maximum	85% R.H.				
	For Air Spray					
	Pressure	2.8-3.0 kg/cm ²				
	Viscosity	34 sec.(Ford cup no.4)				
	Dilution	Not require				
	Mixing Ratio	2 Base : 1 Hardener (by weight)				
	Drying Time					
	Surface Temperature	Touch Dry	Hard Dry	Over coating Interval		Pot Life
				Minimum	Maximum	
	25 °c	6 Hrs	24 Hrs	10 Hrs	--	12 Hrs
	30 °c	4 Hrs	12 Hrs	6 Hrs	--	8 Hrs
	35 °c	2 Hrs	8 Hrs	3 Hrs	--	6 Hrs
ADDITIONAL INFORMATION	Cleaning Solvent	Thinner No.9				
	Packaging	Two pack product				
		18 kg/set				
	Preferable Preceding Coats	-				
	Preferable Subsequent Coats	Siscoguard finish, Siscoguard finish HB, Siscothane AC etc.				
SAFETY PRECAUTIONS	Ensure that there is adequate ventilation in the area where the product is being applied. Do not breath vapour or spray. In case of touch skin, wash skin thoroughly soap and water. In case of accidental eyes splashes, flush eyes with warm water immediately and obtain medical advice.					
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.					