



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสสันส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

SISCOCRETE SC

POLYURETHANE CONCRETE FOR SCRATCH COAT OR AS PRIMING COAT

PRODUCT DESCRIPTION	A 3-component, flowable polyurethane concrete for priming or scratch coat before topcoat with Siscocrete products.	
SPECIFIC PROPERTIES	Sealing porosity of concrete substrate Thermal shock resistance suit for food and beverage industry Fast access time after installation (6 hours-walk on, 5 days-full service) Excellent mechanical and chemical resistance Will not promote bacteria, mold, and fungi growth Breathable finished-allow vapor to evaporate Low odor while installation Easy to clean and maintenance	
PHYSICAL DATA	Colour Specific gravity Consistency Pot life	Cement grey 1.80±0.05 Flowable 15 minutes
APPLICATION DATA	Application method Temperature minimum Mixing & Application Drying time (light traffic) Full cured Recommended thickness Theoretical Coverage	trowel 10 °C Add part A to a clean mixing container follow with part B and mix with helical mixer for 30 seconds. Add part C and mix for further 60-90 seconds until homogeneous mixed is achieved. Apply by trowel or squeegee to the prepared substrate. 6 hours 5 days 1 mm approx. 10-15 m ² /set
ADDITIONAL IMATION	Surface preparation Cleaning Solvent Packaging Storage	Surface should be sound, dry, clean, free from dust, laitance, oil, grease or any contaminations. Solvent 18 kg/set Store in a cool dry place, protect from direct sunlight
SAFETY PRECAUTIONS	Always wear the appropriate safety goggles and gloves during the handling. Properly dispose all used containers and excess material in accordance with the local governing safety rules and regulations. Full information about health, safety and environment of this product are provided in the Materials Safety Data Sheet	
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.	