



SISSONS PAINTS (THAILAND) LTD.

Office : 91/2 moo 3, Suwintawong Rd., Minburi, Bangkok 10510

Tel : 0-2517-1146, 0-2918-6760-1 Fax : 0-2517-2137

ROAD LINE PAINT

TYPE	Chlorinated Rubber with Inert Plasticizer
Color	White , Yellow , Red , black
Glossiness	matt
Reflective	Reflective / Non-Reflective
Solids	By Weight 58 % By Volume 30%
Dry Film Thickness	60 Microns (2.3 Mils) When Applied at Wet Film Thickness of 200 Microns (7.9 Mils)
Coverage (Theoretical)	When Applied at Wet Film Thickness of 200 Microns will be about 19 Square Meter per U.S. Gallon
Coverage (Practical)	Coverage at 20% Loss of Theoretical Coverage is 15 m ² per USG.
Hiding Power	Min. 90%
Drying Time	surface Dry :10-15 Minutes Hard Dry : after 1-2 Hours
Application	By Brush or Spray
Viscosity	75-85 Ku @ 25 °C Stormer Viscometer
Specific Gravity	1.32-1.42
Thinner/ Cleaner	Sissons Thinner No.5
Flash Point	23 °C (or) 40 ° F
Use	For the Marking of concrete and asphalt roads
Surface Condition	Surface to be painted must be dry and clean
Primer	Concrete and Tarmac : Self Primer Steel : Parakol Zinc Chromate Primer Q.D. Industrial Zinc Chromate Primer Wood : Parakol Aluminium Paint
Undercoat	Self Undercoat